

N-50HS (XM-19) Stainless is a high strength and good corrosion resistant austenitic stainless steel. It has more than double the yield strength of 304 and 316 stainless steel and has better corrosion resistance than 317L stainless steel. N-50HS (XM-19) Stainless remains non-magnetic even after being severely cold worked. It maintains strength at high temperatures as well as sub-zero temperatures. The cold worked (HS) version meets the mechanical properties of ASTM A276 Conditions S.

Specifications

UNS: \$20910 **W. Nr./EN:** 1.3964 **ASTM:** A 262, A 276 Condition S, A 370, A 479, A 484 **AMS:** 5764 (chemistry only) **ISO:** 15156-3 **NACE:** MR0175 **API:** API 6A

Chemical Composition, %

	Ni	Cr	Мо	Mn	Si	С	N	S	P	СЬ	V	Fe
MIN	11.5	20.5	1.5	4.0	-	_	0.2	ı	-	0.1	0.1	-
MAX	13.5	23.5	3.0	6.0	1.0	0.06	0.4	0.03	0.045	0.3	0.3	balance

Features

- High strength austenitic alloy
- Good corrosion resistance

Applications

- Seawater pump shafts
- Heat exchangers
- Pressure vessels
- Marine hardware

Physical Properties

Density: 0.285 lb/in³ Melting Range: 2579 - 2642°F Electrical Resistivity: 492 ohm circ-mil/ft

Temperature, °F	70	200	300	400	600	800	900	1000	1200	1400
Coefficient of Thermal Expansion* in/in°F x 10 ⁻⁶	_	9.0	ı	9.2	9.6	9.9	_	10.2	10.5	10.8
Thermal Conductivity Btu • ft/ft² • hr • °F	108	_	108	_	124	-	141	_	160	-
Modulus of Elasticity Dynamic, psi x 10 ⁶	_	26.2	_	-	-	-	-	-	-	_

^{* 70°}F to indicated temperature.

Mechanical Properties

Minimum Specified Properties, ASTM A 276 Condition S Bar

Ultimate Tensile Strength, ksi	135
0.2% Yield Strength, ksi	105
Elongation, %	20
Reduction of Area, %	50
Impact Toughness, ft-lb (-50°F)	30 Min. Average, 20 Min. Single

claudioczarnobai@intwinds.com +55 (11) 3825 2966 www.itwmetals.com.br





CLAUDIO CZARNOBAI COMMERCIAL MANAGER

ClaudioCzarnobai@intwinds.com

F +55 11 3825 2966

C +55 11 99112 2703





www.itwmetals.com.br Bulletin No. 351BZe 09/15

Rolled Alloys, RA are registered trademarks of Rolled Alloys
The data and information in this printed matter are believed to be reliable. However, this material is not intended as a substitute for competent professional engineering assistance which is a requisite to any specific application. Rolled Alloys makes no warranty and assumes no legal liability or responsibility for results to be obtained in any particular situation, and shall not be liable for any direct, indirect, special, or consequential damage therefrom. This material is subject to revision without prior notice.